

# GLASSINE PAPER N

The paper is intended for wrapping of bread and buns, confectionery, food packaging in retail, and lining of packaging for food products containing fat.

## KEY FEATURES & BENEFITS

- Available as SC (supercalendered)
- Available from 24 gsm to 90 gsm, width up to 2500 mm
- Good printability (flexo printing)
- FSC and ISEGA certified
- 100% cellulose = Sustainable and compostable material
- Greaseproof properties
- Unbleached



Glassine Paper

## APPLICATIONS

- Base paper for coating and siliconizing
- Food packaging
- High transparent Glassine 24 gsm suitable for use as window for envelopes and food packaging

## STANDARD SIZES

Grammage	Standard widths	Standard roll diameters	
		Internal Ø	Outside Ø
24 g/m <sup>2</sup>	100, 110, 120 - 370 mm	Ø 76 mm	Ø 400*mm Ø 500 mm (max size)
30 - 90 g/m <sup>2</sup>	290, 380, 740,840 mm	Ø 76 mm	Ø 400*mm Ø 600 mm (max size)

\*Other sizes available by request

# WEIDMANN

## TECHNICAL DATA

Property	Test Method	Unit	Typical Values					
			24 g/m <sup>2</sup>	30 g/m <sup>2</sup>	40 g/m <sup>2</sup>	50 g/m <sup>2</sup>	80 g/m <sup>2</sup>	90 g/m <sup>2</sup>
Grammage	ISO 536	g/m <sup>2</sup>	±3	±2	±2	±3	±5	±7
Density	ISO 534	g/cm <sup>3</sup>	1,00	1,10	1,10	1,10	1,00	1,00
Tensile force, minimum								
- MD	ISO 1924-2	N	30,0	45,0	40,0	65,0	120,0	100,0
- CMD			12,0	20,0	20,0	30,0	50,0	60,0
Bursting strength	ISO 2758	N	60	80	130	170	250	300
Smoothness	ISO 8791/1	sec	-	-	-	-	200/40	150/35
Certification			FSC ISEGA	FSC	FSC	FSC	FSC	FSC

MD = Machine Direction  
 CMD = Cross Machine Direction

Unless specifically stated differently, all data displayed in the table represent typical values only

Rev. 07.23

Weidmann CSM  
 Rapperswil, Switzerland  
 T +41 55 221 41 11

Weidmann CSM  
 St. Johnsbury VT, USA  
 T +1 802 748 8106

Weidmann CSM  
 Shanghai, China  
 T +86 21 3463 7680